




Basic Quality Statistical Summary Report

Plant 1070-Independent South Mine (FDOT Pit#11-298)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 12/23/2024 - 01/03/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	2	99.9	0.14		95-100
#8 (2.36mm)	2	97.8	0.35		85-100
#16 (1.18mm)	2	88.1	2.40	67-98	65-99
#30 (.6mm)	2	64.0	4.03	27-79	25-80
#50 (.3mm)	2	36.8	1.48	7-38	5-40
#100 (.15mm)	2	5.1	0.99	0-6	0-7
#200 (75µm)	2	0.0	0.07		0-4
Pan	2	0.0	0.00		
FM	2	2.083	0.0750	1.87-2.18\2	1.85-2.2
Total Moisture	2	3.785	0.3592		
D10 (ES)	2	0.17	0.000		
D50	2	0.42	0.028		
D60	2	0.54	0.049		
Cc	2	0.74	0.028		
Cu	2	3.28	0.346		



Query

Query Selections
Date Created 01/03/2025
Date Range 12/23/2024 - 01/03/2025
Plant Independent South Mine (FDOT Pit#11-298)
Sample Type Shipping