




# Basic Quality Statistical Summary Report

**Plant** 2010-Ortona Sand Company (FDOT Pit # 05-045)  
**Product** 1009-Concrete Sand  
**Specification** Concrete Sand  
**Period** 12/23/2024 - 01/03/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	100.0	0.00	95-100	
#8 (2.36mm)	5	99.9	0.00	85-100	
#16 (1.18mm)	5	96.2	0.40	65-99	
#30 (.6mm)	5	52.1	2.43	25-70	
#50 (.3mm)	5	14.9	1.27	5-35	
#100 (.15mm)	5	0.9	0.33	0-7	
#200 (75µm)	5	0.0	0.00		
Pan	5	0.0	0.00		
FM	5	2.36	0.014		
Total Moisture	5	3.7	0.20		
D10 (ES)	5	0.23	0.009		
D50	5	0.58	0.021		
D60	5	0.68	0.018		
D15/D85	5	0.30	0.013		
Cc	5	0.99	0.016		
Cu	5	2.87	0.183		



**Query**

Query Selections  
Date Created 01/03/2025  
Date Range 12/23/2024 - 01/03/2025  
Plant Ortona Sand Company (FDOT Pit # 05-045)  
Sample Type Shipping