




Basic Quality Statistical Summary Report

Plant 2010-Ortona Sand Company (FDOT Pit # 05-045)
Product 1008-Mason Sand
Specification Mason Sand
Period 12/23/2024 - 01/03/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	100	0.0	100-100	
#8 (2.36mm)	5	100	0.0	100-100	
#16 (1.18mm)	5	98	0.8	97-100	
#30 (.6mm)	5	80	2.9	80-100	
#50 (.3mm)	5	48	7.7	43-85	
#100 (.15mm)	5	6	4.9	0-25	
#200 (75µm)	5	0.1	0.04		
Pan	5	0.0	0.00		
FM	5	1.67	0.134		
Grad Loss	5	0.000	0.0000		
Total Moisture	5	4.5	0.19	0-5	0-6
D10 (ES)	5	0.16	0.022		
D50	5	0.31	0.037		
D60	5	0.38	0.049		
D15/D85	5	0.24	0.026		
Cu	5	2.43	0.085		



Query

Query Selections
Date Created 01/03/2025
Date Range 12/23/2024 - 01/03/2025
Plant Ortona Sand Company (FDOT Pit # 05-045)
Sample Type Shipping