



02/04/2025

To Whom it may concern,

This material is currently produced at our "Independent" facility (FDOT mine #11-490) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Mason Sand" product number (1008) is a washed and graded product. Each load is accompanied by an individual ticket.

1008-Mason Sand

Procedure	Sieve/Test	Average	Unit	Mason Sand
	#4 (4.75mm)	100	%	
	#8 (2.36mm)	100	%	
	#16 (1.18mm)	100	%	
	#30 (.6mm)	98	%	
	#50 (.3mm)	75	%	
	#100 (.15mm)	16	%	
	#200 (75µm)	0.4	%	
AASHTO T-27	FM	1.11		
AASHTO T-255	Total Moisture	4.0	%	0.0-6.0
	D10 (ES)	0.1148	mm	
	D50	0.22	mm	
	D60	0.25	mm	
	Cc	1.08		
	Cu	2.19		

Sincerely,

Mario Cardenas

Quality Control Manager
E.R. Jahna Ind, Inc.
Office: 352-394-7455
Cell: 863-528-2335
Fax: 352-394-8730

Name/Title

David Clements / Mine manager