



02/04/2025

### 1004-Well Point Sand

Procedure	Sieve/Test	Average	Unit	Well Point Sand
	#4 (4.75mm)	100	%	
	#8 (2.36mm)	100	%	
	#16 (1.18mm)	93	%	
	#30 (.6mm)	38	%	
	#50 (.3mm)	7	%	
	#100 (.15mm)	1	%	
	#200 (75µm)	0.0	%	
ASTM C-136	FM	2.61		
	D10 (ES)	0.32	mm	
	D50	0.70	mm	
	D60	0.78	mm	
	D15/D85	0.34		
	D80/D30	1.99		
	Cc	1.02		
	Cu	2.46		

**Name/Title**

David Clements / Mine manager