




# Basic Quality Statistical Summary Report

**Plant** 1070-Independent South Mine (FDOT Pit#11-298)  
**Product** 1008-Mason Sand  
**Specification** Mason Sand  
**Period** 04/18/2025 - 04/25/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	4	100	0.0	97-100	
#8 (2.36mm)	4	100	0.0	97-100	
#16 (1.18mm)	4	100	0.0	95-100	
#30 (.6mm)	4	99	0.8	85-100	
#50 (.3mm)	4	92	6.4	35-90	
#100 (.15mm)	4	20	3.9	0-35	
#200 (75µm)	4	0.6	0.19		
Pan	4	0.0	0.00		
FM	4	0.901	0.1117	1.05-1.45\1.2	
Total Moisture	4	5.434	1.7580	0-5	0-6
D10 (ES)	4	0.10	0.010		
D50	4	0.20	0.013		
D60	4	0.22	0.013		
Cc	4	1.16	0.066		
Cu	4	2.06	0.079		



**Query**

Query Selections

Date Created 04/25/2025

Date Range 04/18/2025 - 04/25/2025

Plant Independent South Mine (FDOT Pit#11-298)

Sample Type Shipping