




# Basic Quality Statistical Summary Report

**Plant** 2010-Ortona Sand Company (FDOT Pit # 05-045)  
**Product** 1004-Well Point Sand  
**Specification** Well Point Sand  
**Period** 03/18/2025 - 04/18/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	18	100	0.0	100-100	
#8 (2.36mm)	18	100	0.2	85-100	
#16 (1.18mm)	18	93	0.8	50-95	
#30 (.6mm)	18	40	2.8	0-55	
#50 (.3mm)	18	8	1.2	0-35	
#100 (.15mm)	18	1	1.0	0-5	
#200 (75µm)	18	0.0	0.03		
Pan	18	0.0	0.00		
FM	18	2.57	0.041		
D10 (ES)	18	0.31	0.010		
D50	18	0.68	0.022		
D60	18	0.77	0.020		
D15/D85	18	0.33	0.009		
D80/D30	18	2.07	0.071		
Cc	18	0.97	0.054		
Cu	18	2.48	0.071		



**Query**

Query Selections  
Date Created 04/18/2025  
Date Range 03/18/2025 - 04/18/2025  
Plant Ortona Sand Company (FDOT Pit # 05-045)  
Sample Type Shipping