




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 04/18/2025 - 04/25/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	13	100.0	0.00	95-100	
#8 (2.36mm)	13	99.9	0.06	85-100	
#16 (1.18mm)	13	97.1	0.34	65-97	
#30 (.6mm)	13	77.4	2.35	25-75	
#50 (.3mm)	13	43.6	4.04	5-40	
#100 (.15mm)	13	4.4	1.05	0-7	
#200 (75µm)	13	0.1	0.07		
Pan	13	0.0	0.00		
FM	13	1.78	0.062	1.82-2.18\2	1.8-2.2
Grad Loss	13	0.009	0.0176		
Total Moisture	13	3.8	0.93	1-5	1-5
D10 (ES)	13	0.1658	0.00342		
D50	13	0.34	0.025		
D60	13	0.42	0.026		
Cc	13	0.81	0.026		
Cu	13	2.53	0.137		



Query

Query Selections

Date Created 04/25/2025

Date Range 04/18/2025 - 04/25/2025

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping