




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1008-Mason Sand
Specification Mason Sand
Period 04/18/2025 - 04/25/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	4	100	0.0	97-100	
#8 (2.36mm)	4	100	0.0	97-100	
#16 (1.18mm)	4	100	0.0	95-100	
#30 (.6mm)	4	98	0.8	85-100	
#50 (.3mm)	4	94	0.6	35-90	
#100 (.15mm)	4	5	1.5	3-35	
#200 (75µm)	4	0.1	0.00		
Pan	4	0.0	0.00		
FM	4	1.02	0.006	0.9-1.4	1.2
Grad Loss	4	-0.007	0.0135		
Total Moisture	4	3.2	0.17	0-5.5	0-6
D10 (ES)	4	0.1554	0.00167		
D50	4	0.21	0.000		
D60	4	0.23	0.000		
Cc	4	0.92	0.006		
Cu	4	1.48	0.012		



Query

Query Selections

Date Created 04/25/2025

Date Range 04/18/2025 - 04/25/2025

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping