




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1004-Well Point Sand
Specification FLDOT Silica Sand
Period 04/18/2025 - 04/25/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	4	100.0	0.00		95-100
#8 (2.36mm)	4	99.8	0.05		85-100
#16 (1.18mm)	4	92.7	0.22		65-97
#30 (.6mm)	4	42.3	2.24		25-70
#50 (.3mm)	4	2.4	1.66		5-35
#100 (.15mm)	4	0.4	0.49		0-7
#200 (75µm)	4	0.04	0.030		0-4
Pan	4	0.00	0.000		
FM	4	2.62	0.031	2.6	2.55-2.99
Total Moisture	4	3.4	0.17		
D10 (ES)	4	0.3422	0.00926		
D50	4	0.67	0.017		
D60	4	0.76	0.015		
Cu	4	2.22	0.057		



Tests: 1 D10(ES): 0.342 D15: 0.373 D30: 0.485 D50: 0.665 D60: 0.761 D85: 1.064 D90: 1.138 Cu: 2.223 Cc: 0.901

Query

Query Selections

Date Created 04/25/2025

Date Range 04/18/2025 - 04/25/2025

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping