




# Basic Quality Statistical Summary Report

**Plant** 1030-Haines City Mine (FDOT Pit #16-024)  
**Product** 1009-Concrete Sand  
**Specification** Concrete Sand  
**Period** 04/11/2025 - 04/18/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	6	100.0	0.00	95-100	95-100
#8 (2.36mm)	6	99.8	0.05	85-100	85-100
#16 (1.18mm)	6	95.2	0.63	65-98	65-100
#30 (.6mm)	6	71.7	3.11	25-75	≥25
#50 (.3mm)	6	44.5	3.20	5-44	5-45
#100 (.15mm)	6	10.0	0.61	0-10	0-10
#200 (75µm)	6	0.1	0.04	0-4	0-4
Pan	6	0.0	0.00		
FM	6	1.79	0.069	1.8-2.2\2	
Total Moisture	6	4.2	1.18	0-5	0-6
D10 (ES)	6	0.15	0.004		
D50	6	0.34	0.029		
D60	6	0.45	0.034		
Cc	6	0.76	0.005		
Cu	6	3.01	0.254		



**Query**

Query Selections

Date Created 04/18/2025

Date Range 04/11/2025 - 04/18/2025

Plant Haines City Mine (FDOT Pit #16-024)

Sample Type Shipping