




Basic Quality Statistical Summary Report

Plant 1030-Haines City Mine (FDOT Pit #16-024)
Product 1008-Mason Sand
Specification Mason Sand
Period 04/18/2025 - 04/25/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	7	100	0.0	97-100	
#8 (2.36mm)	7	100	0.0	97-100	
#16 (1.18mm)	7	100	0.5	90-100	
#30 (.6mm)	7	97	4.1	65-100	
#50 (.3mm)	7	81	10.9	35-90	
#100 (.15mm)	7	16	4.2	0-40	
#200 (75µm)	7	0.2	0.10		
Pan	7	0.0	0.00		
FM	7	1.06	0.187		
Total Moisture	7	4.2	0.93	0-6\3	0-7
D10 (ES)	7	0.12	0.015		
D50	7	0.22	0.019		
D60	7	0.24	0.022		
Cc	7	1.08	0.089		
Cu	7	2.06	0.067		



Tests: 1 D10(ES): 0.115 D15: 0.144 D30: 0.174 D50: 0.216 D60: 0.240 D85: 0.357 D90: 0.443 Cu: 2.080 Cc: 1.097

Query

Query Selections

Date Created 04/25/2025

Date Range 04/18/2025 - 04/25/2025

Plant Haines City Mine (FDOT Pit #16-024)

Sample Type Shipping