




# Basic Quality Statistical Summary Report

**Plant** 1210-Savannah Sand Mine  
**Product** 117-GDOT 10NS Concrete Sand  
**Specification** GADOT 10NS  
**Period** 04/18/2025 - 04/25/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
3/8" (9.5mm)	10	100.00	0.000		
#4 (4.75mm)	10	99.58	0.181		95-100
#8 (2.36mm)	10	94.29	0.659		
#16 (1.18mm)	10	78.06	3.693		45-95
#30 (.6mm)	10	47.26	6.885		
#50 (.3mm)	10	19.03	7.432		5-30
#100 (.15mm)	10	5.13	2.959		0-10
#200 (75µm)	10	0.21	0.099		0-3
Pan	10	0.00	0.000		
FM	10	2.56	0.201	2.4-2.85\2.65	
Grad Loss	10	0.002	0.0076		
Total Moisture	10	4.8	1.28	0-5\4	0-6
D10 (ES)	10	0.20	0.050		
D50	10	0.63	0.094		
Cu	10	3.93	0.571		



Tests: 1 D10(ES): 0.191 D15: 0.245 D30: 0.393 D50: 0.637 D60: 0.794 D85: 1.587 D90: 1.965 Cu: 4.150 Cc: 1.016

**Query**

Query Selections  
Date Created 04/25/2025  
Date Range 04/18/2025 - 04/25/2025  
Plant Savannah Sand Mine  
Sample Type Shipping