




# Basic Quality Statistical Summary Report

**Plant** 1210-Savannah Sand Mine  
**Product** 1008-Mason Sand  
**Specification** Mason Sand  
**Period** 04/18/2025 - 04/25/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	6	100	0.0	97-100	
#8 (2.36mm)	6	100	0.0	97-100	
#16 (1.18mm)	6	99	0.4	90-100	
#30 (.6mm)	6	95	1.3	65-100	
#50 (.3mm)	6	80	3.0	35-90	
#100 (.15mm)	6	20	3.7	0-40	
#200 (75µm)	6	0.6	0.15		
Pan	6	0.0	0.00		
FM	6	1.06	0.076		
Total Moisture	6	6.2	2.50	0-6\3	0-7
D10 (ES)	6	0.11	0.008		
D50	6	0.21	0.008		
D60	6	0.24	0.008		
Cc	6	1.12	0.028		
Cu	6	2.23	0.096		



**Query**

Query Selections  
Date Created 04/25/2025  
Date Range 04/18/2025 - 04/25/2025  
Plant Savannah Sand Mine  
Sample Type Shipping