




# Basic Quality Statistical Summary Report

**Plant** 1050-Independent North Mine (FDOT Pit #11-490)  
**Product** 1008-Mason Sand  
**Specification** Mason Sand  
**Period** 05/01/2025 - 05/08/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	3	100	0.0	97-100	
#8 (2.36mm)	3	100	0.0	97-100	
#16 (1.18mm)	3	100	0.0	95-100	
#30 (.6mm)	3	98	0.6	85-100	
#50 (.3mm)	3	69	2.6	35-90	
#100 (.15mm)	3	9	1.5	0-35	
#200 (75µm)	3	0.3	0.10		
Pan	3	0.0	0.00		
FM	3	1.24	0.046	1.05-1.45\1.2	
Total Moisture	3	3.0	0.93	0-5	0-6
D10 (ES)	3	0.1488	0.00765		
D50	3	0.24	0.006		
D60	3	0.27	0.010		
Cc	3	0.91	0.029		
Cu	3	1.82	0.065		



**Query**

Query Selections  
Date Created 05/08/2025  
Date Range 05/01/2025 - 05/08/2025  
Plant Independent North Mine (FDOT Pit #11-490)  
Sample Type Shipping