




Basic Quality Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1008-Mason Sand
Specification Mason Sand
Period 05/23/2025 - 05/30/2025

| Sieve/Test | Tests | Average | St Dev | Target | Specification |
|----------------|-------|---------|--------|---------------|---------------|
| #4 (4.75mm) | 1 | 100 | | 97-100 | |
| #8 (2.36mm) | 1 | 100 | | 97-100 | |
| #16 (1.18mm) | 1 | 98 | | 95-100 | |
| #30 (.6mm) | 1 | 91 | | 85-100 | |
| #50 (.3mm) | 1 | 69 | | 35-90 | |
| #100 (.15mm) | 1 | 18 | | 0-35 | |
| #200 (75µm) | 1 | 0.4 | | | |
| Pan | 1 | 0.0 | | | |
| FM | 1 | 1.24 | | 1.05-1.45\1.2 | |
| Total Moisture | 1 | 4.0 | | 0-5 | 0-6 |
| D10 (ES) | 1 | 0.1086 | | | |
| D50 | 1 | 0.23 | | | |
| D60 | 1 | 0.27 | | | |
| Cc | 1 | 1.07 | | | |
| Cu | 1 | 2.44 | | | |



Query

Query Selections

Date Created 05/30/2025

Date Range 05/23/2025 - 05/30/2025

Plant Independent North Mine (FDOT Pit #11-490)

Sample Type Shipping