




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 05/23/2025 - 05/30/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	9	100.0	0.00	95-100	
#8 (2.36mm)	9	99.9	0.05	85-100	
#16 (1.18mm)	9	96.5	0.79	65-97	
#30 (.6mm)	9	74.8	4.08	25-75	
#50 (.3mm)	9	39.2	4.11	5-40	
#100 (.15mm)	9	3.2	0.72	0-7	
#200 (75µm)	9	0.1	0.11		
Pan	9	0.0	0.00		
FM	9	1.86	0.078	1.82-2.18\2	1.8-2.2
Grad Loss	9	0.035	0.0706		
Total Moisture	9	3.6	0.57	1-5	1-5
D10 (ES)	9	0.1713	0.00329		
D50	9	0.37	0.026		
D60	9	0.45	0.030		
Cc	9	0.83	0.056		
Cu	9	2.63	0.134		



Query

Query Selections

Date Created 05/30/2025

Date Range 05/23/2025 - 05/30/2025

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping