




# Basic Quality Statistical Summary Report

**Plant** 1130-Green Bay Mine (FDOT Pit #16-608)  
**Product** 1001-FDOT Concrete Silica Sand Code F01  
**Specification** FLDOT Silica Sand  
**Period** 05/23/2025 - 05/30/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	7	100	0.0	95-100	95-100
#8 (2.36mm)	7	100	0.0	85-100	85-100
#16 (1.18mm)	7	95	0.5	67-96	65-97
#30 (.6mm)	7	66	2.2	27-68	25-70
#50 (.3mm)	7	23	2.2	7-33	5-35
#100 (.15mm)	7	1	0.0	0-6	0-7
#200 (75µm)	7	0	0.0	0-4	0-4
Pan	7	0	0.0		
FM	7	2.15	0.031	2.3	2.1-2.5
-#200 (75um)	1	0.06			
Grad Loss	7	0.052	0.0790		
Wash Loss (#200/75um)	1	0.06			
Total Moisture	7	3.5	0.67		
Color	1	2			1-5
D10 (ES)	7	0.1993	0.00563		
D50	7	0.46	0.014		
D60	7	0.55	0.017		
Cc	7	1.03	0.027		
Cu	7	2.74	0.100		



**Query**

Query Selections

Date Created 05/30/2025

Date Range 05/23/2025 - 05/30/2025

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping