




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1008-Mason Sand
Specification Mason Sand
Period 05/23/2025 - 05/30/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	100	0.0	97-100	
#8 (2.36mm)	5	100	0.0	97-100	
#16 (1.18mm)	5	100	0.0	95-100	
#30 (.6mm)	5	98	0.4	85-100	
#50 (.3mm)	5	71	4.0	35-90	
#100 (.15mm)	5	8	1.1	3-35	
#200 (75µm)	5	0.1	0.04		
Pan	5	0.0	0.00		
FM	5	1.23	0.038	0.9-1.4	1.2
Grad Loss	5	0.000	0.0000		
Total Moisture	5	3.3	0.59	0-5.5	0-6
D10 (ES)	5	0.1543	0.00156		
D50	5	0.24	0.010		
D60	5	0.27	0.010		
Cc	5	0.90	0.005		
Cu	5	1.73	0.070		



Query

Query Selections

Date Created 05/30/2025

Date Range 05/23/2025 - 05/30/2025

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping