




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1004-Well Point Sand
Specification FLDOT Silica Sand
Period 05/23/2025 - 05/30/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	100.0	0.00		95-100
#8 (2.36mm)	5	99.8	0.04		85-100
#16 (1.18mm)	5	91.1	0.94		65-97
#30 (.6mm)	5	40.1	1.54		25-70
#50 (.3mm)	5	3.1	1.17		5-35
#100 (.15mm)	5	0.3	0.34		0-7
#200 (75µm)	5	0.02	0.013		0-4
Pan	5	0.00	0.000		
FM	5	2.66	0.023	2.6	2.55-2.99
Total Moisture	5	2.9	0.45		
D10 (ES)	5	0.3412	0.00612		
D50	5	0.69	0.011		
D60	5	0.78	0.012		
Cu	5	2.29	0.055		



Query

Query Selections

Date Created 05/30/2025

Date Range 05/23/2025 - 05/30/2025

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping