




# Basic Quality Statistical Summary Report

**Plant** 1070-Independent South Mine (FDOT Pit#11-298)  
**Product** 1009-Concrete Sand  
**Specification** Concrete Sand  
**Period** 04/08/2025 - 05/08/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	14	99.8	0.27		95-100
#8 (2.36mm)	14	98.7	0.74		85-100
#16 (1.18mm)	14	91.2	2.65	67-98	65-99
#30 (.6mm)	14	70.1	6.28	27-79	25-80
#50 (.3mm)	14	44.6	11.74	7-38	5-40
#100 (.15mm)	14	8.7	3.49	0-6	0-7
#200 (75µm)	14	0.1	0.06		0-4
Pan	14	0.0	0.00		
FM	14	1.868	0.2388	1.87-2.18\2	1.85-2.2
Total Moisture	14	4.856	2.6486		
D10 (ES)	14	0.15	0.020		
D50	14	0.36	0.073		
D60	14	0.45	0.099		
Cc	14	0.83	0.138		
Cu	14	2.95	0.388		



**Query**

Query Selections  
Date Created 05/08/2025  
Date Range 04/08/2025 - 05/08/2025  
Plant Independent South Mine (FDOT Pit#11-298)  
Sample Type Shipping