




Basic Quality Statistical Summary Report

Plant 1070-Independent South Mine (FDOT Pit#11-298)
Product 1008-Mason Sand
Specification Mason Sand
Period 04/08/2025 - 05/08/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	11	100	0.0	97-100	
#8 (2.36mm)	11	100	0.0	97-100	
#16 (1.18mm)	11	100	0.3	95-100	
#30 (.6mm)	11	99	0.5	85-100	
#50 (.3mm)	11	91	6.7	35-90	
#100 (.15mm)	11	19	5.9	0-35	
#200 (75µm)	11	0.5	0.24		
Pan	11	0.0	0.00		
FM	11	0.913	0.0783	1.05-1.45\1.2	
Total Moisture	10	5.720	1.5539	0-5	0-6
D10 (ES)	11	0.11	0.015		
D50	11	0.20	0.009		
D60	11	0.22	0.010		
Cc	11	1.12	0.072		
Cu	11	2.02	0.237		



Query

Query Selections
Date Created 05/08/2025
Date Range 04/08/2025 - 05/08/2025
Plant Independent South Mine (FDOT Pit#11-298)
Sample Type Shipping