




# Basic Quality Statistical Summary Report

**Plant** 1070-Independent South Mine (FDOT Pit#11-298)  
**Product** 1009-Concrete Sand  
**Specification** Concrete Sand  
**Period** 06/13/2025 - 06/20/2025

| Sieve/Test   | Tests | Average | St Dev | Target | Specification |
|--------------|-------|---------|--------|--------|---------------|
| #4 (4.75mm)  | 1     | 99.8    |        |        | 95-100        |
| #8 (2.36mm)  | 1     | 99.3    |        |        | 85-100        |
| #16 (1.18mm) | 1     | 93.8    |        | 67-98  | 65-99         |
| #30 (.6mm)   | 1     | 74.6    |        | 27-79  | 25-80         |
| #50 (.3mm)   | 1     | 49.8    |        | 7-38   | 5-40          |
| #100 (.15mm) | 1     | 9.3     |        | 0-6    | 0-7           |
| #200 (75µm)  | 1     | 0.1     |        |        | 0-4           |
| Pan          | 1     | 0.0     |        |        |               |



**Query**

Query Selections

Date Created 06/20/2025

Date Range 06/13/2025 - 06/20/2025

Plant Independent South Mine (FDOT Pit#11-298)

Product

Specification Auto-Default

Number of Tests 30