




Basic Quality Statistical Summary Report

Plant 1070-Independent South Mine (FDOT Pit#11-298)
Product 1001-FDOT Concrete Silica Sand Code F01
Specification FLDOT Silica Sand
Period 06/13/2025 - 06/20/2025

| Sieve/Test | Tests | Average | St Dev | Target | Specification |
|--------------|-------|---------|--------|--------|---------------|
| #4 (4.75mm) | 10 | 100 | 0.0 | 95-100 | 95-100 |
| #8 (2.36mm) | 10 | 99 | 0.5 | 85-100 | 85-100 |
| #16 (1.18mm) | 10 | 90 | 1.5 | 67-96 | 65-97 |
| #30 (.6mm) | 10 | 61 | 3.2 | 27-68 | 25-70 |
| #50 (.3mm) | 10 | 26 | 3.3 | 7-33 | 5-35 |
| #100 (.15mm) | 10 | 3 | 0.7 | 0-7 | 0-7 |
| #200 (75µm) | 10 | 0 | 0.0 | 0-4 | 0-4 |
| Pan | 10 | 0 | 0.0 | | |



Query

Query Selections

Date Created 06/20/2025

Date Range 06/13/2025 - 06/20/2025

Plant Independent South Mine (FDOT Pit#11-298)

Product

Specification Auto-Default

Number of Tests 30