




# Basic Quality Statistical Summary Report

**Plant** 1050-Independent North Mine (FDOT Pit #11-490)  
**Product** 1009-Concrete Sand  
**Specification** Concrete Sand  
**Period** 06/13/2025 - 06/20/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	9	100.0	0.00		95-100
#8 (2.36mm)	9	99.8	0.07		85-100
#16 (1.18mm)	9	96.2	0.83	67-98	65-99
#30 (.6mm)	9	76.0	3.52	27-79	25-80
#50 (.3mm)	9	26.6	1.56	7-38	5-40
#100 (.15mm)	9	1.3	0.36	0-6	0-7
#200 (75µm)	9	0.1	0.05		0-4
Pan	9	0.0	0.00		



**Query**

Query Selections

Date Created 06/20/2025

Date Range 06/13/2025 - 06/20/2025

Plant Independent North Mine (FDOT Pit #11-490)

Product

Specification Auto-Default

Number of Tests 30