




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 06/02/2025 - 06/09/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	11	100.0	0.00	95-100	
#8 (2.36mm)	11	99.9	0.05	85-100	
#16 (1.18mm)	11	97.5	0.50	65-97	
#30 (.6mm)	11	78.7	3.73	25-75	
#50 (.3mm)	11	42.1	5.19	5-40	
#100 (.15mm)	11	3.9	0.77	0-7	
#200 (75µm)	11	0.1	0.12		
Pan	11	0.0	0.00		
FM	11	1.78	0.088	1.82-2.18\2	1.8-2.2
Grad Loss	11	0.025	0.0565		
Total Moisture	11	3.7	0.73	1-5	1-5
D10 (ES)	11	0.1680	0.00376		
D50	11	0.35	0.030		
D60	11	0.42	0.034		
Cc	11	0.84	0.051		
Cu	11	2.50	0.150		



Query

Query Selections

Date Created 06/09/2025

Date Range 06/02/2025 - 06/09/2025

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping