




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1004-Well Point Sand
Specification FLDOT Silica Sand
Period 06/02/2025 - 06/09/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	3	100.0	0.00		95-100
#8 (2.36mm)	3	99.8	0.06		85-100
#16 (1.18mm)	3	92.4	1.10		65-97
#30 (.6mm)	3	43.3	0.35		25-70
#50 (.3mm)	3	1.3	0.15		5-35
#100 (.15mm)	3	0.1	0.12		0-7
#200 (75µm)	3	0.07	0.066		0-4
Pan	3	0.00	0.000		
FM	3	2.63	0.010	2.6	2.55-2.99
Total Moisture	3	3.0	0.06		
D10 (ES)	3	0.3464	0.00104		
D50	3	0.66	0.000		
D60	3	0.76	0.006		
Cu	3	2.18	0.010		



Query

Query Selections

Date Created 06/09/2025

Date Range 06/02/2025 - 06/09/2025

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping