




Basic Quality Statistical Summary Report

Plant 1030-Haines City Mine (FDOT Pit #16-024)
Product 1008-Mason Sand
Specification Mason Sand
Period 06/02/2025 - 06/09/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	7	100	0.0	97-100	
#8 (2.36mm)	7	100	0.0	97-100	
#16 (1.18mm)	7	100	0.0	90-100	
#30 (.6mm)	7	99	1.2	65-100	
#50 (.3mm)	7	88	3.9	35-90	
#100 (.15mm)	7	17	2.9	0-40	
#200 (75µm)	7	0.2	0.12		
Pan	7	0.0	0.00		
FM	7	0.95	0.063		
Total Moisture	6	5.9	0.96	0-6\3	0-7
D10 (ES)	7	0.13	0.049		
D50	7	0.21	0.005		
D60	7	0.23	0.007		
Cc	7	1.05	0.228		
Cu	7	1.90	0.422		



Tests: 1 D10(ES): 0.112 D15: 0.138 D30: 0.170 D50: 0.207 D60: 0.228 D85: 0.291 D90: 0.340 Cu: 2.031 Cc: 1.131

Query

Query Selections

Date Created 06/09/2025

Date Range 06/02/2025 - 06/09/2025

Plant Haines City Mine (FDOT Pit #16-024)

Sample Type Shipping