




Basic Quality Statistical Summary Report

Plant 2010-Ortona Sand Company (FDOT Pit # 05-045)
Product 1008-Mason Sand
Specification Mason Sand
Period 06/02/2025 - 06/09/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	4	100	0.0	100-100	
#8 (2.36mm)	4	100	0.0	100-100	
#16 (1.18mm)	4	100	0.0	97-100	
#30 (.6mm)	4	98	1.0	80-100	
#50 (.3mm)	4	85	2.2	43-85	
#100 (.15mm)	4	11	1.3	0-25	
#200 (75µm)	4	0.2	0.13		
Pan	4	0.0	0.00		
FM	4	1.06	0.047		
Grad Loss	4	0.038	0.0453		
Total Moisture	4	6.1	1.36	0-5	0-6
D10 (ES)	4	0.14	0.008		
D50	4	0.22	0.005		
D60	4	0.24	0.005		
D15/D85	4	0.49	0.022		
Cu	4	1.70	0.106		



Query

Query Selections

Date Created 06/09/2025

Date Range 06/02/2025 - 06/09/2025

Plant Ortona Sand Company (FDOT Pit # 05-045)

Sample Type Shipping