




# Basic Quality Statistical Summary Report

**Plant** 1210-Savannah Sand Mine  
**Product** 117-GDOT 10NS Concrete Sand  
**Specification** GADOT 10NS  
**Period** 06/02/2025 - 06/09/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
3/8" (9.5mm)	6	100.00	0.000		
#4 (4.75mm)	6	99.64	0.173		95-100
#8 (2.36mm)	6	94.29	1.261		
#16 (1.18mm)	6	77.59	4.115		45-95
#30 (.6mm)	6	47.46	6.241		
#50 (.3mm)	6	17.18	6.037		5-30
#100 (.15mm)	6	3.42	1.821		0-10
#200 (75µm)	6	0.21	0.126		0-3
Pan	6	0.00	0.000		
FM	5	2.64	0.180	2.4-2.85\2.65	
Grad Loss	5	0.000	0.0000		
Total Moisture	5	4.1	0.29	0-5\4	0-6
D10 (ES)	5	0.23	0.054		
D50	5	0.65	0.080		
Cu	5	3.60	0.502		



Tests: 1 D10(ES): 0.209 D15: 0.269 D30: 0.402 D50: 0.635 D60: 0.795 D85: 1.605 D90: 1.975 Cu: 3.805 Cc: 0.974

**Query**

Query Selections  
Date Created 06/09/2025  
Date Range 06/02/2025 - 06/09/2025  
Plant Savannah Sand Mine  
Sample Type Shipping