




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1001-FDOT Concrete Silica Sand Code F01
Specification FLDOT Silica Sand
Period 09/11/2026 - 09/18/2026

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	11	100	0.0	95-100	95-100
#8 (2.36mm)	11	100	0.0	85-100	85-100
#16 (1.18mm)	11	95	0.5	67-96	65-97
#30 (.6mm)	11	62	3.1	27-68	25-70
#50 (.3mm)	11	18	8.4	7-33	5-35
#100 (.15mm)	11	2	2.4	0-6	0-7
#200 (75µm)	11	0	0.0	0-4	0-4
Pan	11	0	0.0		
FM	11	2.228	0.0992	2.3	2.1-2.5
Total Moisture	11	3.287	0.7205		



Query

Query Selections

Date Created 09/18/2026

Date Range 09/11/2026 - 09/18/2026

Plant Green Bay Mine (FDOT Pit #16-608)

Product

Specification Auto-Default

Number of Tests 30