




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1004-Well Point Sand
Specification FLDOT Silica Sand
Period 09/11/2026 - 09/18/2026

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	7	100.0	0.00		95-100
#8 (2.36mm)	7	100.0	0.05		85-100
#16 (1.18mm)	7	92.6	1.10		65-97
#30 (.6mm)	7	47.8	7.31		25-70
#50 (.3mm)	7	1.8	1.23		5-35
#100 (.15mm)	7	0.3	0.23		0-7
#200 (75µm)	7	0.01	0.020		0-4
Pan	7	0.00	0.000		
FM	7	2.576	0.0875	2.6	2.55-2.99



Query

Query Selections

Date Created 09/18/2026

Date Range 09/11/2026 - 09/18/2026

Plant Green Bay Mine (FDOT Pit #16-608)

Product

Specification Auto-Default

Number of Tests 30