




Basic Quality Statistical Summary Report

Plant 1030-Haines City Mine (FDOT Pit #16-024)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 09/11/2026 - 09/18/2026

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	6	100.0	0.00	95-100	95-100
#8 (2.36mm)	6	99.5	0.31	85-100	85-100
#16 (1.18mm)	6	93.7	3.16	65-98	65-100
#30 (.6mm)	6	65.7	8.40	25-75	≥25
#50 (.3mm)	6	38.7	7.34	5-44	5-45
#100 (.15mm)	6	9.1	2.52	0-10	0-10
#200 (75μm)	6	0.2	0.05	0-4	0-4
Pan	6	0.0	0.00		
FM	6	1.932	0.1889	1.78-2.2\2	
Total Moisture	6	4.628	0.7106	0-5	0-6



Query

Query Selections

Date Created 09/18/2026

Date Range 09/11/2026 - 09/18/2026

Plant Haines City Mine (FDOT Pit #16-024)

Product

Specification Auto-Default

Number of Tests 30