




Basic Quality Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1008-Mason Sand
Specification Mason Sand
Period 09/11/2026 - 09/18/2026

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	4	100	0.0	97-100	
#8 (2.36mm)	4	100	0.0	97-100	
#16 (1.18mm)	4	99	0.8	95-100	
#30 (.6mm)	4	93	4.0	85-100	
#50 (.3mm)	4	73	13.7	35-90	
#100 (.15mm)	4	12	2.1	0-35	
#200 (75µm)	4	0.2	0.05		
Pan	4	0.0	0.00		
FM	4	1.238	0.2023	1.05-1.45\1.2	
Total Moisture	4	4.411	1.0844	0-5	0-6



Query

Query Selections

Date Created 09/18/2026

Date Range 09/11/2026 - 09/18/2026

Plant Independent North Mine (FDOT Pit #11-490)

Product

Specification Auto-Default

Number of Tests 30