




Basic Quality Statistical Summary Report

Plant 2010-Ortona Sand Company (FDOT Pit # 05-045)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 09/11/2026 - 09/18/2026

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	4	100.0	0.00	95-100	
#8 (2.36mm)	4	99.9	0.10	85-100	
#16 (1.18mm)	4	96.2	0.44	65-99	
#30 (.6mm)	4	57.8	2.21	25-70	
#50 (.3mm)	4	22.5	3.23	5-35	
#100 (.15mm)	4	12.3	1.28	0-7	
#200 (75µm)	4	0.0	0.06		
Pan	4	0.0	0.00		
FM	4	2.115	0.0638		
Total Moisture	4	3.664	0.6943		



Query

Query Selections

Date Created 09/18/2026

Date Range 09/11/2026 - 09/18/2026

Plant Ortona Sand Company (FDOT Pit # 05-045)

Product